


TEST REPORT

Lightwater Quarries Ltd
Potgate Quarry
North Stainley
Ripon
HG4 3JN



White
Rose
Laboratory
Services
Ltd

Lumley St • Castleford • WF10 5LB
01977 520625 • enquiries@whiteroselabs.co.uk

Report WRL/17/2970fi
Issue date 19/12/17

Material	Crushed limestone aggregate 20/10mm		
Site	Potgate Quarry		
Specification	EN12620 10/20 G_C 85/20 f_4	Sample N°	S/17/2970
Source	Potgate Quarry	Sampled by	S Tallentire/ L Rowling
Supplier	Lightwater Quarries Ltd	Date sampled	11/12/17
Sample location	End of belt	Date received	11/12/17
Sample type	Bulk	Date tested	18/12/17
Order number	8815LQ	Date reported	19/12/17

BS EN 933-3 2012 Flakiness Index

Mass of test portion 4216 g

Flakiness Index 5.1

A handwritten signature in black ink, appearing to read 'J Church'.

J Church
Managing Director